



**TITAN HI-STRENGTH MASONRY CEMENT
MEETS OR EXCEEDS ASTM C-91
MIXING GUIDELINES**

TITAN H.S. MASONRY TYPE	80 lbs	SAND (Arena)		BLOCKS PER BAG (Bloques por Saco)
		PARTS (Partes)	SHOVELS (Palas)	
M	1 BAG	2 1/2 - 3	15 - 18	66 -75
S	1 BAG	3 - 4	18 - 24	75 - 96

NO ALLOWANCE FOR WASTE
FIELD CONDITIONS MAY CAUSE VARIANCES IN COVERAGE PER BAG

ADD MINIMUM QUANTITY OF CLEAN WATER AND MIX FOR A MINIMUM OF 3-5 MINUTES TO ACHIEVE MORTAR
CONSISTENCY FOR PROPER PLACEMENT

TITAN HI-STRENGTH MASONRY CEMENT WHEN MIXED WITH MASONRY SAND (ASTM c-144) AND TESTED
ACCORDING TO THE PROPERTY SPECIFICATION SECTION OF ASTM C-270 WILL PRODUCE A MORTAR THAT
COMPLIES WITH THE REQUIREMENTS FOR TYPE "M" AND "S" MASONRY.