



<b>TITAN WHITE MASONRY CEMENT MEETS OR EXCEEDS ASTM C-91 MIXING GUIDELINES</b>			
<b>TYPE</b>	<b>TITAN WHITE MASONRY 70lbs</b>	<b>SAND ( Arena )</b>	
		<b>PARTS ( Partes )</b>	<b>SHOVELS ( Palas )</b>
<b>S</b>	<b>1 BAG</b>	<b>2 1/2 - 3</b>	<b>15 - 18</b>
<b>N</b>	<b>1 BAG</b>	<b>3 - 4</b>	<b>18 - 24</b>

ADD MINIMUM QUANTITY OF CLEAN WATER AND MIX FOR A MINIMUM OF 3 TO 5 MINUTES TO ACHIEVE MORTAR CONSISTENCY FOR PROPER PLACEMENT

**TITAN** WHITE MASONRY CEMENT WHEN MIXED WITH MASONRY SAND (ASTM C-144) AND TESTED ACCORDING TO THE PROPERTY SPECIFICATION SECTION OF (ASTM C-270) WILL PRODUCE A MORTAR THAT COMPLIES WITH THE REQUIREMENTS FOR TYPES 'S' AND 'N' MASONRY.