



**TITAN PORTLAND CEMENT TYPE  
ASTM C - 150**

**MIXING GUIDELINES**

**PARTS BY VOLUME  
( Partes por Volumen)**

<b>CEMENT</b>	<b>(Cemento)</b>	<b>1</b>
<b>SAND</b>	<b>(Arena)</b>	<b>2</b>
<b>GRAVEL OF STONE</b>	<b>(Gravilla)</b>	<b>3</b>

**THIS MIX WILL YIELD 5.17 CUBIC FEET OR 15 SQUARE FEET OF CONCRETE AT 4 INCHES THICK**

**USE NO MORE THAN 5 1/2 GALLONS OF WATER PER BAG OF CEMENT.  
MIX THOROUGHLY AND CURE BY KEEPING IT DAMP FOR 4 TO 7 DAYS**