



<b>TITAN ROOF TILE CEMENT            MEETS OR EXCEEDS ASTM C-91            MIXING GUIDELINES</b>			
<b>TYPE</b>	<b>TITAN ROOF TILE            78 lbs</b>	<b>SAND ( Arena )</b>	
		<b>PARTS            ( Partes )</b>	<b>SHOVELS            ( Palas )</b>
<b>M</b>	<b>1 BAG</b>	<b>2 1/2 - 3</b>	<b>15 - 18</b>

ADD MINIMUM QUANTITY OF CLEAN WATER AND MIX FOR A MINIMUM OF 3 TO 5 MINUTES TO ACHIEVE MORTAR CONSISTENCY FOR PROPER PLACEMENT

**TITAN** ROOF TILE CEMENT WHEN MIXED WITH MASONRY SAND (ASTM C-144) AND TESTED ACCORDING TO (ASTM C-270) WILL PRODUCE A MORTAR THAT COMPLIES WITH THE REQUIREMENTS FOR TYPE 'M' MASONRY.